

PLASTICIZERS DERIVED FROM VEGETABLE OILS

CLAIMS

We claim:


- 1 (1) A plasticized vinyl chloride composition, comprising:
2 (a) about 100 parts by weight of at least one vinyl chloride resin;
3 (b) about 10 to 230 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer
5 comprises a fatty acid product derived from a vegetable oil having
6 at least 80% by weight of unsaturated fatty acids, wherein said
7 fatty acids are substantially fully esterified with a monool or a
8 polyol, and said esterified unsaturated fatty acids have been
9 substantially fully epoxidized;
10 (c) said vegetable oil derived plasticizers composition comprising,
11 (1) said fatty acid product derived from direct esterification of fatty
12 acids of said vegetable oil with a monool or a polyol;
13 (2) said fatty acid product derived from transesterification of said
14 vegetable oil with monools or polyols;
15 (3) said fatty acid product derived from said vegetable oil
16 interesterified with another vegetable oil having a higher degree of
17 unsaturation; mixtures of the above; or
18 (4) said fatty acid product derived from a fatty acids from said
19 vegetable oil esterified with a monool and interesterified with a
20 polysaccharide carboxylic acid ester. .
1
1 (2) The composition of claim 1, wherein said plasticized vinyl chloride
2 composition is essentially free of DOP.
1

1 (3) The composition of claim 1, wherein when said alcohol is a polyol and
2 said fatty acids derived from said vegetable oil are substantially
3 randomly positioned on the hydroxyl sites of said polyol.

1 (4) The composition of claim 1, wherein said vegetable oil is selected from
2 the group consisting of,
3 canola oil (I.V. value about 100-115),
4 corn oil (I.V. value about 118-128),
5 linseed oil (I.V. value about 170-200),
6 rapeseed oil (I.V. value about 100-115),
7 safflower oil (I.V. value about 140-150),
8 soybean oil (I.V. value about 120-143),
9 sunflower oil (I.V. value about 125-140),
10 tall oil (I.V. value about 140-190), and
11 tung oil (I.V. value about 180) (and mixtures of derivatives thereof) and
12 mixtures thereof.

1 (5) The composition of claim 1, wherein said plasticizer composition is
2 derived from a vegetable oil having an iodine value above about 100.


1 (6) The composition of claim 1, wherein said plasticizer composition is
2 epoxidized pentaerythritol tetrasoyate having the formula:



3
4
5
6
7
8 wherein R (each of the R's may be the same or different) is randomly
9 selected from the group consisting of:

- 10 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
11 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
12 and margaroyl.


1 (7) The composition of claim 1, wherein said composition is epoxidized
2 propylene glycol disoyate having the formula:



3
4 wherein R (each of the R's may be the same or different) is randomly
5 selected from the group consisting of:

- 6 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
7 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
8 and margaroyl.


1
1 (8) The composition of claim 1, wherein said composition is epoxidized
2 ethylene glycol disoyate having the formula:



3
4
5
6
7 wherein R (each of the R's may be the same or different) is randomly
8 selected from the group consisting of:

- 9 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
10 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
11 and margaroyl.


1
1 (9) The composition of claim 1, wherein said plasticizer composition is a
2 mixture of epoxidized methyl soyate having the formula:



3
4
5 wherein R is randomly selected from the group consisting of:

- 6 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
7 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
8 and margaroyl.

- 1 (10) The composition of claim 1, wherein said composition is epoxidized
2 sucrose octasoyate having the formula:




3
4 wherein R (each of the R's may be the same or different) is selected
5 from the group consisting of:

- 6 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
7 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
8 and margaroyl.

- 1
1 (11) The composition of claim 1, wherein each R is randomly selected from
2 said group.

- 1
1 (12) The composition of claim 1, wherein said composition is the epoxidized
2 product of a first vegetable oil interesterified with a second vegetable oil,
3 and having the formula:




4
5
6
7
8
9 wherein R (each of the R's may be the same or different) is randomly
10 selected from the group consisting of:

- 11 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
12 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
13 and margaroyl.

- 1
1 (13) The composition according to Claim 12, wherein said first vegetable oil
2 has an iodine value greater than 100 and the second vegetable oil
3 has an iodine value greater than the first vegetable oil.

1
1 (14) The composition of claim 12, wherein said first vegetable oil is soybean
2 oil, and said second vegetable oil is linseed oil.


1
2
3 (15) Epoxidized pentaerythritol tetrasoyate having the formula:



7 wherein R (each of the R's may be the same or different) is randomly
8 selected from the group consisting of:

- 9 (i) substantially fully epoxidized unsaturated fatty acids derived from a
10 vegetable oil; or
11 (ii) non-epoxidized saturated fatty acids derived from a vegetable oil;
12 wherein said vegetable oil has greater than about 80% unsaturated fatty
13 acids and/or an iodine number above about 100.


1
1 (16) Epoxidized propylene glycol disoyate having the formula:



2
3 wherein R (each of the R's may be the same or different) is randomly
4 selected from the group consisting of:

- 5 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
6 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
7 and margaroyl.


1
1 (17) Epoxidized ethylene glycol disoyate having the formula:



7 wherein R (each of the R's may be the same or different) is randomly
8 selected from the group consisting of

- 9 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
10 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
11 and margaroyl.


1
1 (18) Epoxidized methyl soyate having the formula:



2
3 wherein R is randomly selected from the group consisting of:

- 4 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
5 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
6 and margaroyl.
7

1
1 (19) Epoxidized sucrose octasoyate having the formula:




4 wherein R (each of the R's may be the same or different) is selected
5 from the group consisting of:

- 6 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
7 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
and margaroyl.

1
1 (20) The composition of claim 1, wherein each R is randomly selected from
2 said group.

1
1 (21) The epoxidized product of a first vegetable oil interesterified with a
2 second vegetable oil having the formula:



6
7

8 wherein R (each of the R's may be the same or different) is randomly
9 selected from the group consisting of:

- 10 (i) epoxidized linoleoyl, oleoyl, linolenoyl, and palmitoleoyl; or
11 (ii) non-epoxidized palmitoyl, stearoyl, arachidoyl, behenoyl, myristoyl,
12 and margaroyl.

1

1 (22) The composition of claim 21, wherein said first vegetable oil is soybean
2 oil, and said second vegetable oil is linseed oil.

1

1 (23) A plasticized vinyl chloride composition, comprising:

- 2 (a) about 100 parts by weight of at least one vinyl chloride resin;
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is
5 epoxidized pentaerythritol tetrasoyate; and
6 (c) about 1-3 parts thermal stabilizer compounded with said at least
7 one vinyl chloride resin and said plasticizer.

1

1 (24) A plasticized vinyl chloride composition, comprising:

- 2 (a) about 100 parts by weight of at least one vinyl chloride resin;
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is
5 epoxidized propylene glycol disoyate; and
6 (c) about 1-3 parts thermal stabilizer compounded with said at least
7 one vinyl chloride resin and said plasticizer.

1

1

- 1 (25) A plasticized vinyl chloride composition, comprising:
2 (a) about 100 parts by weight of at least one vinyl chloride resin;
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is
5 epoxidized ethylene glycol disoyate; and
6 (c) about 1-3 parts thermal stabilizer compounded with said at least
7 one vinyl chloride resin and said plasticizer.

- 1 (26) A plasticized vinyl chloride composition, comprising:
2 (a) about 100 parts by weight of at least one vinyl chloride resin;
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is
5 epoxidized methyl soyate; and
6 (c) about 1-3 parts thermal stabilizer compounded with said at least
7 one vinyl chloride resin and said plasticizer.

- 1 (27) A plasticized vinyl chloride composition, comprising:
2 (a) about 100 parts by weight of at least one vinyl chloride resin;
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is
5 epoxidized sucrose octasoyate; and
6 (c) about 1-3 parts thermal stabilizer.

- 1 (28) A plasticized vinyl chloride composition, comprising
2 (a) about 100 parts by weight of at least one vinyl chloride resin; and
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is the
5 epoxidized product of a first ester interesterified with a second
6 ester; and
7 (c) about 1-3 parts thermal stabilizer compounded with said at least
8 one vinyl chloride resin and said plasticizer.

- 1 (29)A plasticized vinyl chloride composition, comprising
2 (a) about 100 parts by weight of at least one vinyl chloride resin; and
3 (b) about 10 to 100 parts by weight of a plasticizer compounded with
4 said at least one vinyl chloride resin, wherein said plasticizer is the
5 epoxidized product of a first vegetable oil interesterified with a
6 second vegetable oil; and
7 (c) about 1-3 parts thermal stabilizer compounded with said at least
8 one vinyl chloride resin and said plasticizer.

1

- 1 (30) The composition of claim 28, wherein said first vegetable oil is soybean
2 oil, and said second vegetable oil is linseed oil.

1

204033 P 2054050